
SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Blå Station
Surface:	Ginkgo

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.15
250	0.6
500	0.9
1000	0.8
2000	0.75
4000	0.7
α_w	0.80
NRC	0.75



ORIGINAL TEST REPORT	DATE OF REPORT
14-117-M2	2014-08-26

Acoustic Facts Scandinavia AB

Kinnegatan 23, 531 33 Lidköping

acousticfacts.com