
SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:

Surface: Reindeer Moss CONVEX

Octave band (Hz)	Sound absorption coefficient (-)
63	0.1
125	0.25
250	0.65
500	1
1000	1
2000	1
4000	1
α_w	0.95
NRC	0.90



Frequency, Hz

ORIGINAL TEST REPORT	DATE OF REPORT
19-725-M3	2019-12-18

Acoustic Facts Scandinavia AB

Kinnegatan 23, 531 33 Lidköping

acousticfacts.com