




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

**Client:** BAUX AB  
**Surface:** BAUX Acoustic Pulp

Octave band (Hz)	Sound absorption coefficient (-)
63	0
125	0.05
250	0.1
500	0.55
1000	0.45
2000	0.3
4000	0.25
<b><math>\alpha_w</math> 0.35</b>	
<b>NRC 0.35</b>	



ORIGINAL TEST REPORT

Akustikverkstan report 18-723-M1

DATE OF REPORT

2019-01-07

