




SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	Parafon
Surface:	Parafon® Step for Grids
Suspension Height:	w = 400

Octave band (Hz)	Sound absorption coefficient (-)
63	0.15
125	0.6
250	0.75
500	0.85
1000	1
2000	1
4000	1
α_w	0.95
NRC	0.90



ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 17-322-M20	2017-12-15

