
SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

Client:	
Surface:	Basic Wall 116x116
Suspension Height:	w = 0

Octave band (Hz)	Sound absorption coefficient (-)
63	0.1
125	0.25
250	0.55
500	0.9
1000	1
2000	1
4000	1
α_w	0.85
NRC	0.85



Frequency, Hz

ORIGINAL TEST REPORT	DATE OF REPORT
Akustikverkstan report 21-701-M3	2021-03-15

Acoustic Facts Scandinavia AB

Kinnegatan 23, 531 33 Lidköping

acousticfacts.com