




# SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

<b>Client:</b>	Götessons/ Gotessons, Akustikmiljö / Am Acoustics		
<b>Object:</b>	PlainPanel (2 groups of 6 pcs)		
<b>Size [mm]:</b>	w = 58	h = 58	d = 21

Octave band (Hz)	Equivalent sound absorption area / unit (m <sup>2</sup> Sabine)
63	0.04
125	0.15
250	0.54
500	1.1
1000	1.8
2000	2
4000	1.9
<b>N<sub>10</sub> = 9.1</b>	



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 22-702-M4	2022-02-11

