
SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to ISO 354 and ISO 20189

Client:	Boom Interior		
Object:	Xrozz Absorption Recycled		
Size [mm]:	w = 800	h = 1000	d = 40

Octave band (Hz)	Equivalent sound absorption area / unit (m^2Sabine)
63	0.25
125	0.35
250	0.56
500	0.7
1000	0.81
2000	1
4000	1.24
N_{10} =	14.3



ORIGINAL TEST REPORTS	DATE OF REPORT
Akustikverkstan report 20-240M2	2020-06-24
Akustikverkstan report 18-701-M3	2018-08-23

The presented results are interpolated using the method described in ISO 20189 from the original test reports.

Acoustic Facts Scandinavia AB

Kinnegatan 23, 531 33 Lidköping

acousticfacts.com