




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive A 18 mm
<b>Suspension Height:</b>	w = 0

Octave band (Hz)	Sound absorption coefficient (-)
63	0
125	0.05
250	0.1
500	0.45
1000	0.8
2000	0.95
4000	1
$\alpha_w$	0,40(MH)
NRC	0.60



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 10-55-M143	2010-11-19

