




# SOUND ABSORPTION COEFFICIENT

Measured and evaluated according to ISO 354 and ISO 11654

<b>Client:</b>	Parafon
<b>Surface:</b>	PARAFON Exclusive A 18 mm
<b>Suspension Height:</b>	w = 50

Octave band (Hz)	Sound absorption coefficient (-)
63	0.05
125	0.1
250	0.35
500	0.8
1000	1
2000	1
4000	1
$\alpha_w$	0,65(MH)
NRC	0.80



<b>ORIGINAL TEST REPORT</b>	<b>DATE OF REPORT</b>
Akustikverkstan report 10-55-M144	2010-11-19

