


## SOUND ABSORPTION AREA FOR OBJECT

Measured and evaluated according to SS-EN ISO 354 and SS 25269

CLIENT: Abstracta AB  
 OBJECT: Softline Bordsskärm (Desk screen with mineral wool)  
 Size [mm]:  $w = 600$     $h = 650$     $t = 50$

1/3 octave band (Hz)	Equivalent sound absorption area / unit (m <sup>2</sup> Sabine)	
	1/3 octave band	Octave band
50	0,04	
63	0,07	0,1
80	0,13	
100	0,06	
125	0,14	0,1
160	0,12	
200	0,29	
250	0,31	0,3
315	0,32	
400	0,46	
500	0,49	0,5
630	0,64	
800	0,68	
1000	0,62	0,6
1250	0,64	
1600	0,61	
2000	0,61	0,6
2500	0,61	
3150	0,66	
4000	0,61	0,7
5000	0,69	



### CONDITIONS

Date of test: 2015-04-10      Object area: 0,4      m<sup>2</sup>  
 Date: 2016-08-15      Rev. room volume: 200      m<sup>3</sup>

Test report: **15-065-M4**  
 Signature: Delphine Bard